

LEGIBILITY NOTICE

A major purpose of the Technical Information Center is to provide the broadest dissemination possible of information contained in DOE's Research and Development Reports to business, industry, the academic community, and federal, state and local governments.

Although portions of this report are not reproducible, it is being made available in microfiche to facilitate the availability of those parts of the document which are legible.

LA-UR

Received by OSTI

AUG 06 1990

Los Alamos National Laboratory is operated by the University of California for the United States Department of Energy under contract number W-7405-ENG-26

LA-UR--90-2431

DE90 014905

TITLE IS THERE ANYTHING OF PRACTICAL VALUE HIDDEN AMONGST
THE COMPOSITE TOUGHENING TRIEDS? - A JIM MUELLER
PERSPECTIVE

AUTHOR(S) Frank J. Mueller

SUBMITTED TO American Ceramic Society for publication in the
proceedings of the 14th Annual Conference on
Composites and Advanced Ceramics, January 14-17, 1990,
Orlando Beach, Florida

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

This report is made available to the public under the terms of the Public Law 94-173, which authorizes the United States Government to publish and reproduce the contents of this report for the United States Government purposes.

When a report is published by the publisher, identify it as work performed under the auspices of the United States Department of Energy.

Los Alamos Los Alamos National Laboratory
Los Alamos, New Mexico 87545

IS THERE ANYTHING OF PRACTICAL VALUE HIDDEN AMONGST THE
COMPOSITE TOUGHENING THEORIES?! - A JIM MUELLER PERSPECTIVE*

Frank D. Gac**

Los Alamos National Laboratory
Ceramic Science & Technology Group
Los Alamos National Laboratory
Los Alamos, New Mexico 87545

ABSTRACT

Numerous theories have been developed over the last three decades for explaining the toughening behavior of discontinuous fiber reinforced brittle matrix composites. The issue is the practical engineering utility of these theories. Upon compiling a table of fiber parameters that are identified in the predominant toughening mechanisms, a number of important features become evident for achieving high toughnesses. First, all of the mechanisms indicate that a high fiber volume fraction is desirable. Second, residual stresses appear to influence all of the composite toughening mechanisms. Third, the highest fiber tensile strength is preferred. Finally, fiber diameter and fiber-matrix interfacial shear strength are also important, but both are composite system and toughening mechanism specific.

1. INTRODUCTION

It is a tremendous honor to present the 1990 James I. Mueller Memorial lecture. It is especially flattering to be the first student of Jim's to do such.

Nearly four years have passed since his death. It is a certainty that many of you knew Jim and it is also likely that some of you have little or no idea who this man was.

*Presented at the 14th Annual Conference on Composites and Advanced Ceramics, sponsored by the Engineering Ceramics Division of the American Ceramic Society, Cocoa Beach, FL, January 15, 1990 (James I. Mueller Memorial Lecture).

**Member, American Ceramic Society.

The following brief biography will stir up memories for some and provide new information for others.

James I. Mueller was born to August L. and Lydia (Heyn) Mueller on June 26, 1916 (Figure 1.). Jim received his B.S. in 1939 from Ohio State University and his Ph.D. in 1949 from the University of Missouri-Rolla. Both degrees were in Ceramic Engineering.

Jim's accomplishments and awards were many. His career was centered around the University of Washington, which he joined in 1949 as an Assistant Professor, with the assignment of developing a Ceramic Engineering curriculum (Figure 2.). As a result of his efforts, the Ceramic Engineering Division was created within what was then the Department of Mining, Metallurgical and Ceramic Engineering, and is now termed the Department of Materials Science & Engineering. Many a renowned student have been produced by that department over the years, and "Doc," as his students affectionately called him, no doubt influenced all of them. One example is Astronaut Dr. Bonnie J. Dunbar, who during the presentation of this lecture was orbiting the earth aboard the Space Shuttle Columbia! Bonnie was part of a five member crew tasked with two primary objectives, 1) the deployment of SYNCOM, a communications satellite, and most importantly from the standpoint of materials types, 2) the

The author did not realize until preparing this lecture that his son, Benjamin Thomas Gar, and James I. Mueller share the same birthday. Benjamin, however, arrived on the scene 64 years later.

long awaited retrieval of the Long Duration Exposure Facility or LDEF.

Space, what an exciting frontier! Doc was best known for his interest in the space program (Figure 3.). Between the years of 1963 to 1987, he received continuous funding from NASA totalling nearly eight million dollars (\$8 M). That translates to roughly two hundred and forty thousand dollars (\$240 k) per year. One especially noteworthy outcome from that research was the development of an innovative, new, interdisciplinary program entitled Brittle Materials Design. In fact, it was that program that attracted the author to the University of Washington to pursue a Ph.D. Yet another noteworthy development was the research Jim directed on addressing the attachment problems associated with the Space Shuttle's thermal protection tiles. This work resulted in Jim being awarded NASA's Public Service Medal in 1981.

Jim was also a devoted member of the American Ceramic Society. One cannot begin to review all of the committees and programs he participated in. Suffice it to say, however, that Jim's efforts did not go unnoticed. He was recognized both as a Fellow and a Distinguished Life Member of the American Ceramic Society, received numerous other awards, and served as the President of the Society in 1981-1982.

Finally, Jim had a propensity for the practical. He displayed an impressive ability to identify national and

worldwide trends in materials and boil these trends down to practical issues. These issues might be technical or administrative in nature, which having been identified could then be addressed by an individual or preferably a team of individuals. Today's "Cocoa Beach Meeting," the Engineering Ceramics Division of the American Ceramic Society, and the United States Advanced Ceramics Association or USACA (Jim, incidentally, was USACA's first president in 1985) were no doubt heavily influenced by Jim Mueller's foresight and propensity for the practical.

The next section will demonstrate how Jim Mueller's practical perspective pervades the author's approach to ceramic engineering, and more specifically influenced a topic of particular interest to the attendees of the 14th Annual Meeting on Composites and Advanced Ceramic Materials, namely, ceramic composite development. The question at hand is, "Is there anything of practical value hidden amongst the composite toughening theories?"

II. COMPOSITE TOUGHENING MECHANISMS

Numerous concepts have been proposed for toughening and to a certain extent, for strengthening of ceramic matrix composites. All of the concepts can be generalized into one or more of three basic mechanisms, as illustrated in Figure 4. One mechanism embodies increasing the local driving force necessary to propagate a crack to failure. This could be accomplished by imposing a compressive stress state on

the ceramic, for example, by shrink fitting a metallic sleeve around a ceramic rod. A second mechanism involves increasing the mechanical energy consumed per unit area of crack propagation. The incorporation of a ductile phase in a ceramic would satisfy this criteria because mechanical energy would be consumed in plastically deforming the ductile phase during crack propagation. The third mechanism involves decreasing the local strain by cracking, which reduces the crack tip stress concentration. Matrix microcracking without catastrophic fracture obviously satisfies this criteria. The issue, of course, is what is the engineering utility of the microcracked composite.

The predominant toughening concepts are enumerated in Figure 5. The remainder of this lecture will elaborate on the practical fundamentals of most of these concepts and culminate with a table that one can use as a guide for the development of fiber or whisker reinforced ceramic matrix composites.

1. Modulus Transfer

This mechanism operates on the basis of transferring the applied load from a lower elastic modulus matrix to the higher elastic modulus fibers, to achieve strain uniformity within the structure (i.e., strain in composite = fiber strain = matrix strain). A strong, non-slipping fiber-matrix interface is required for this mechanism to operate effectively.

For a composite reinforced with continuous, unidirectionally aligned fibers, the corresponding stress in the composite is given by¹:

$$\sigma_c = \sigma_m \left[(1 - V_f) + V_f \frac{E_f}{E_m} \right] \quad (1)$$

where σ_c is the stress in the composite, σ_m is the stress in the matrix, V_f is the volume fraction of fibers, and E_f and E_m are the modulus of elasticity of the fiber and matrix, respectively. Examination of this expression reveals that the greatest improvement in the composite strength would occur when the elastic modulus of the fiber is much greater than the elastic modulus of the matrix. In addition, the higher the fiber volume fraction the better (up to a practical limit, of course).

A potential composite that could benefit from the modulus transfer concept is the silicon carbide (SiC) whisker - reaction bonded silicon nitride (RBSN) matrix system. The elastic modulus of VLS SiC whiskers has been reported to be 581 GPa (84.3 Mpsi)² and that of RBSN is reported to vary over the range of 97-221 GPa (14.1-32.1 Mpsi).³ Thus, the elastic modulus of the SiC whiskers is 3-6 times greater than that of the RBSN. Hence, strengthening by the modulus transfer concept is conceivable. The difficulty arises in maintaining the SiC whisker integrity during RBSN fabrication.

Toughening is accomplished through this concept simply because an increase in local driving force is required to propagate a crack through the composite system, as increased load is being accommodated by the fiber. When dealing with discontinuous fiber or whisker reinforced composites, one must also address the load that a given length fiber can bear and the stress concentrations that occur at the fiber ends. This concept was nicely illustrated by Schuster¹² in a composite consisting of a 25 μm diameter by 3000 μm long sapphire whisker in a photoelastic resin matrix, as shown in Figure 6. The elastic modulus ratio of the whisker to the matrix is approximately 125. The matrix stress reduction along the length of the whisker is roughly a factor of two, whereas the stress is intensified at the whisker tips by a factor of three.

2. Fiber Pull-out

An expression has been developed for the fiber pull-out theory which defines the maximum work-of-fracture (WOF) one can achieve in a composite.⁷⁻¹² This is important because the WOF is an indication of the toughness (or more specifically, the R-curve behavior) of the composite. The expression is:

$$\text{WOF}_p = \frac{V_f \sigma_f^2 r_f}{12\tau} \quad (2)$$

where WOF_p is the maximum work-of-fracture for fiber pull-out, r_f is the fiber radius, τ is the fiber-matrix

interfacial shear strength, and all other terms are as previously defined. This expression states that the composite "toughness" will be enhanced with large values of fiber volume fraction, high fiber strength, a small interfacial shear strength, and, interestingly enough, a large fiber radius.

3. Crack Bridging

Another important toughening concept that is receiving a lot of attention is crack bridging. The crack bridging theory^{11,12} postulates that intact reinforcements behind the primary crack front will bridge the crack surfaces in the following wake region, thus inhibiting further crack opening and reducing the stress intensity at the crack tip. Evans and McMeeking¹² have proposed three bounding solutions for this model: 1) frictional bridging resulting from an unbonded fiber, 2) strong particle bridging, and 3) ductile particle bridging.

a. Frictional Bridging (Figure 7.) When the reinforcing fibers are unbonded and fiber motion is restrained by friction, then the critical stress intensity factor (toughness), K_{IC} , for frictional bridging can be approximated by:

$$K_{IC} \approx (\sigma_f^3 G / 3 E_f r) \frac{1}{2} \sqrt{r_f A_f} \quad (3)$$

where G is the elastic shear modulus of the composite, A_f is the areal fraction of reinforcements on the crack plane (an

indication of the volume fraction of reinforcements) and all other terms are as previously defined.

b. Strong Particle Bridging (Figure 8.) The critical stress intensity factor for the strong particle bridging case is approximated by:

$$K_c \approx 1.1 \sigma_f \sqrt{r_f A_f (1 - \sqrt{A_f})(1 - A_f)} \quad (4)$$

where now the "f" subscript simply refers to the reinforcement, be it a whisker or a particle. This expression represents the situation where the interfacial shear strength goes to infinity, such as for whiskers that are strongly bonded to a matrix. It should be noted that the bridging particle does not need to be tougher than the matrix for this mechanism to operate. It must only be stronger.

c. Ductile Particle Bridging (Figure 9.) When the particle is "tougher" than the matrix, the situation can be described by a ductile-particle-extension bridging mechanism. The expression for that critical stress intensity factor is approximated by:

$$K_c \approx \sqrt{\Omega C A_f \sigma_y G_{rf} (0.5 + \exp(\epsilon_f))} \quad (5)$$

where Ω is an empirical factor related to the ductility and size of the ductile particle, C is a constraint factor that is believed to be of the order of 6-8 for crack pinning by

ductile particle reinforcement, σ_p is the yield stress of the particle, ϵ_p is the particle failure strain, and all other terms are as previously defined.

One central result emerges from these three crack bridging mechanisms. Namely, that toughening will increase with increasing reinforcement strength, increasing reinforcement size or diameter, and increasing reinforcement volume fraction.

4. Crack Arresting/Blunting

Yet another toughening mechanism is crack arresting or blunting. On one hand, it can be viewed as a generalized form of crack bridging, in that it represents the extreme case where the particles have sufficient strength and toughness to completely resist fracture. On the other hand, it represents a situation where crack propagation is eliminated by removing the stress concentration at the crack tip, such as by introducing a hole (e.g., a circular or spherical pore) ahead of a propagating crack. The issue is one of composite performance criteria. A particle which displays sufficient toughness to arrest cracking at ambient temperature, e.g., a metal, may be much too plastic and/or lack environmental resistance at elevated temperatures. Conversely, refractory reinforcements are typically brittle at ambient temperature, and thus, lack the fracture toughness necessary to completely arrest fracture in that temperature regime. Finally, the presence of porosity may

be advantageous from the standpoint of toughness but can have an undesirable affect on strength.

5. Crack Bowing

The crack bowing concept^{14, 15} is related to crack bridging in that it is also a crack impediment process. As described by Faber and Evans¹⁷:

"Crack bowing originates from resistant second phase particles in the path of a propagating crack. The crack tends to bow between the particles, causing the stress intensity along the bowed segment of the crack to decrease (while resulting in a corresponding increase in the stress intensity at the particle). The degree of bowing increases until the fracture toughness of the particle is reached, whereupon crack advance ensues."

The crack bowing concept is illustrated in Figure 10., with a sketch taken from a publication by Lange.¹⁴ In this work, Lange proposed a model for crack bowing that was based upon the hypothesis that a crack front possesses a line energy similar to a dislocation. The result of this work is contained in the following equation:

$$G_c = 2 \left(\gamma_0 + \frac{T}{D} \right) \quad (6)$$

where G_c is the amount of energy required to extend a crack a unit length (i.e., the fracture energy), γ_0 is the surface

energy of the matrix material, T is the line energy per unit length of crack front, and D is the distance between the second phase particles. This expression indicates that a brittle material's resistance to fracture, i.e., toughness, increases with a decreasing mean free path between the particles, and hence, an increasing volume fraction of particles. This implies a particle size dependence in that at a given volume fraction, smaller particles will provide for more crack pinning sites per unit volume. Lange also concluded that significant toughening does not occur unless the particle spacing is significantly less than the flaw size.

6. Crack Deflection

The crack deflection concept¹²⁻¹⁴ is related to the crack bowing concept in that it similarly addresses the interaction of a propagating crack with a second phase inclusion or particle. The distinction lies in the fact that crack deflection produces a non-planar (twisted) crack, as illustrated in Figure 11., whereas crack bowing only produces a non-linear crack front. The non-planar crack arises either from residual stresses present in the material and/or from the existence of weakened interfaces.

Faber and Evans¹²⁻¹⁴ conducted a systematic study of crack deflection in an attempt to develop a model for the phenomenon. The model is based on fracture mechanic principles and basically consists of two parts, a crack tilt function and a crack twist function. They assumed that when

a crack approaches or intercepts a microstructural inhomogeneity, it will tilt at an angle that depends on the orientation and position of the particle with respect to the advancing crack, as well as upon the nature of the residual stress that may be present between the particle and the matrix. The tilted crack is subject to mixed-mode local loading, characterized by Mode I (opening) and Mode II (sliding) contributions to the stress intensity. Faber and Evans then assumed that subsequent advance of the crack may result in crack front twist and additional tilt, depending on the orientation, position and stress state of adjacent particles. The twisted crack contains both Mode I and Mode III (tearing) stress intensity components. They proposed that the increase in fracture toughness imparted by crack deflection could then be determined by evaluating the local stress intensities at the tilted and twisted portions of the crack front. Faber and Evans proceeded with this analysis and also incorporated particle morphology effects by investigating three dominant morphologies: a sphere, a rod, and a disk.

As a result of their analysis of crack deflection, Faber and Evans¹⁷ presented a number of important conclusions. The increase in toughness imparted by crack deflection depends on particle shape and the volume fraction of the second phase. The most effective particle morphology for deflecting cracks is the rod of "high" aspect ratio. However, the toughening increase tends to saturate at aspect

ratios greater than about 12. Similarly, toughening saturates at fiber volume fractions of about 20%. The Faber-Evans analysis also predicted that toughening will be independent of fiber size. However, some question exists on this prediction, since at a given volume fraction, smaller particles will provide for more crack interaction sites. Finally, the Faber-Evans analysis made no prediction as to the effect of interfacial bond strength on toughening, although it is certainly understood that weakened interfaces directly influence the propensity for crack deflection.

7. Matrix Microcracking

The phenomenon of matrix microcracking occurs because of thermal expansion differences, phase transformations and differences in elastic moduli between the matrix and a second phase. ^{11,12} The refractories industry has capitalized on microcracking for years to achieve thermal shock resistant bodies. The microcracks in these systems are often pre-existing and large in size, resulting in relatively weak bodies. In more recent years, the generation of small microcracks at, or near, a main crack tip has become a topic of interest. Microcracks occur from the superposition of the high tensile stresses concentrated near the crack tip with the intrinsic mismatch stresses, resulting in a microcracked "process" zone around the crack tip, as illustrated in Figure 12.

A first order estimate of the upper bound of fracture energy increase, G_{max} , due to microcracking (per unit area

of advance of the main crack) was determined by Rice.²¹ The result is presented in equation (7):

$$\Delta G_{mc} = \frac{2\pi a \gamma_{mc} V_f L}{d} \quad (7)$$

where L and aL are the major and minor axes of an elliptical microcrack process zone (a is < 1), γ_{mc} is the microcrack interfacial fracture energy, V_f is the volume fraction of second phase particles, and d is the diameter of the second phase particles. Thus, G_{mc} is directly proportional to the boundary fracture energy, the volume fraction of particles which induce the microcracks, and the process zone size. It is inversely proportional to the diameter of the particles.

8. Residual Stress Effects

The importance of elastic modulus differences have already been discussed, and the influence of phase transformations and thermal expansion differences have been alluded to. Residual stresses resulting from thermal expansion differences merit additional discussion.

Thermal expansion differences can result in residual stresses which may directly influence the load bearing and toughening characteristics of a composite. For a two-dimensional problem in plane strain consisting of a circular reinforcement particle (fiber) embedded in an infinite matrix, the fiber experiences a radial stress, σ_r , which can be approximated by²²:

$$\sigma_r = \frac{(\alpha_m - \alpha_f)\Delta TE_m}{(1 + \nu_m) + (1 + \nu_f)(E_m/E_f)} \quad (8)$$

where α_m is the thermal expansion coefficient of the matrix, α_f is the thermal expansion coefficient of the fiber, T is the change in temperature, ν_m is the Poisson's ratio of the matrix, ν_f is the Poisson's ratio of the fiber, and E_m and E_f are the same as previously defined.

When $\alpha_f > \alpha_m$, cooling from the processing temperature places the fiber in tension and the matrix in compression. Silicon carbide whiskers in a silicon nitride or cordierite matrix are examples of this situation. In this scenario, an increased local driving force would be necessary for crack propagation to occur through the matrix. If the fiber-matrix mismatch is too large and/or the interfacial bond is too weak, then cracks may develop around the fiber, essentially debonding the fiber from the matrix. This could be beneficial to toughening by a fiber pull-out mechanism, but it would probably inhibit significant strengthening. Another point to consider is that if the interfacial bond strength is so large that the matrix is maintained in compression, then the fiber is "pre-loaded" in tension. This may reduce the overall tensile load that the fiber can sustain within the composite and the strength of the composite may not achieve its optimal level.

If the $\alpha_f < \alpha_m$, cooling from the processing temperature places the fiber in compression and the matrix in tension.

This is the situation for SiC whiskers reinforcing alumina, mullite, molybdenum disilicide, magnesium aluminate spinel or zirconia matrices. This scenario is believed to enhance toughening by matrix microcracking and crack multiplication. It could also enhance toughening by promoting crack bridging by the fiber, since greater applied stresses must be imposed on the fibers to attain their fracture stresses.

9. Summary of Toughening Theory Predictions

Table 1 summarizes the toughening predictions for discontinuous fiber reinforced ceramic matrix composites. From the practical materials engineering viewpoint, a number of features are evident in this tabular summary. First, all mechanisms dictate that a high fiber volume fraction is desirable for achieving maximum toughness; i.e., "more is better." Hence, processing research should be directed at effectively incorporating high volume loadings (at least 10 and preferably >20 vol%) of fibers within ceramic matrices. Second, residual stresses appear to influence all of the composite toughening mechanisms, although few relationships have been developed for quantitatively predicting the residual stresses or their effects on composite toughness. Thus, research is warranted in this area. In spite of this lack of predictive capabilities, the competent ceramic matrix composite designer should at least be cognizant of the influence that residual stresses may have on his composite system. Third, it appears that the highest fiber tensile strength is advantageous; i.e., "stronger is

better." Thus, a high strength, single crystal SiC whisker would be preferred over a chopped, polycrystalline SiC fiber, whose strength is inherently lower. Finally, the fiber diameter and fiber-matrix interfacial shear strength also appear to be important, but both are composite system and toughening mechanism specific.

III. CLOSING REMARKS

This lecture was configured so that it would be of value to the novice and expert alike. Thus, it is the author's hope that all who read this manuscript might identify a nugget or preferably a motherload of useful information on composite development. In response to the question, "Is there anything of practical value hidden amongst the composite toughening theories!!", the answer is, "Yes, absolutely!" The likely follow-up response from "Doc" might be, "So, what are you doing sitting on your ____?!" Get out there and do something!" (Figure 13.7).

IV. REFERENCES

1. D. K. Shetty, "Ceramic Matrix Composites," Current Awareness Bulletin, No. 118, pp. 1-4, Metals and Ceramics Information Center, Battelle Columbus Laboratories, Columbus, OH, December 1982.
2. J. J. Petrovic, J. J. Milewski, D. L. Rohr and F. D. Gac, "Tensile Mechanical Properties of SiC Whiskers," J. Mater. Sci., 20 (4) 1167-77 (1985).
3. Engineering Property Data on Selected Ceramics, Volume I, Nitrides, Metals and Ceramics Information Center report MCIC-HB-07-Vol. 1 (March 1976).

4. D. M. Donister, "Single and Multi-Fiber Interactions in Discontinuous Reinforced Composites," Ph.D. thesis, Cornell University, 1967.
5. A. M. Little, "Strong Solids," *Proc. Roy. Soc., A261*, 2-5 (1964).
6. A. Kelly, "The Strengthening of Metals by Dispersed Particles," *ibid.*, 63-73 (1964).
7. G. A. Cooper, "The Fracture Toughness of Composites Reinforced with Weakened Fibers," *J. Mater. Sci.*, 5 545-54 (1970).
8. D. M. Hale and A. Kelly, "Strength of Fibrous Composite Materials," *Ann. Rev. Mater. Sci.*, 2 445-62 (1972).
9. G. A. Cooper, "Micromechanics Aspects of Fracture and Toughness," pp. 41-48 in *Composite Materials, Fracture and Fatigue*, Vol. 1, E. L. G. Broutman and R. M. Brock, Eds., Academic Press, New York, 1974.
10. F. F. Lange, "Fracture Mechanics and Microstructural Design," pp. 79-919 in *Fracture Mechanics of Ceramics*, Vol. 1, R. L. Bradi, D. P. H. Hasselman and F. F. Lange, Eds., Plenum Press, New York, 1973.
11. B. Budiansky, "Micromechanics II," Harvard University, Division of Applied Sciences report MEI-81, June 1986; presented at the Tenth U.S. National Congress of Applied Mechanics, The University of Texas, Austin, Texas, June 16-20, 1986.
12. A. G. Evans and J. M. McMeeking, "On the Toughening of Ceramics by Strong Reinforcements," *Acta Met.*, 34 (12) 2435-41 (1986).
13. V. V. Krstic, P. S. Nicholson and R. J. Hoagland, "Toughening of Glasses by Metallic Particles," *ibid.*, 34 (3) 499-504 (1987).
14. F. F. Lange, "The Interaction of a Crack Front with a Second-Phase Dispersion," *Philos. Mag.*, 12 933-92 (1975).
15. A. G. Evans, "The Strength of Brittle Materials Containing Second Phase Dispersions," *Philos. Mag.*, 26 161 1327-44 (1972).
16. D. J. Green, "Fracture Toughness Predictions for Crack Bowing in Brittle Particulate Composites," *J. Am. Ceram. Soc.*, 66 (1) C4-C5 (1983).

17. K. T. Faber and A. G. Evans, "Crack Deflection Processes - I. Theory," *Acta Met.*, 31 665-76 (1983).
18. K. T. Faber and A. G. Evans, "Crack Deflection Processes - II. Experiment," *Acta Met.*, 31 677-94 (1983).
19. K. T. Faber and A. G. Evans, "Intergranular Crack-Deflection Toughening in Silicon Carbide," *Comm. Am. Ceram. Soc.*, 66 (6) C94-C96 (1983).
20. D. H. Carter and G. F. Hurley, "Crack Deflection as a Toughening Mechanism in SiC-Whisker-Reinforced MoSi₂," *Comm. Am. Ceram. Soc.*, 70 (4) C70-C81 (1987).
21. R. W. Rice, "Mechanisms of Toughening in Ceramic Composites," *Ceram. Eng. Sci. Proc.*, 2 (7-8) 661-701 (1981).
22. J. J. Cleveland and R. T. Bradt, "Grain Size/Microcracking Relations for Pseudobrookite Oxides," *J. Am. Ceram. Soc.*, 61 (11-12) 478-81 (1978).
23. R. W. Rice and R. D. Pohanka, "Grain-Size Dependence of Spontaneous Cracking in Ceramics," *J. Am. Ceram. Soc.*, 62 (11-12) 559-63 (1979).
24. A. G. Evans and K. T. Faber, "Toughening of Ceramics by Circumferential Microcracking," *J. Am. Ceram. Soc.*, 64 (7) 394-98 (1981).
25. H. T. Loren, "Micromechanics and Fracture Behavior of Composites," in *Modern Composite Materials*, L. J. Broutman and R. H. Krock, Eds., Addison-Wesley, Reading, Massachusetts, 1967, Chap. 2, pp. 23-30.

FIGURE CAPTIONS

1. Abbreviated vita of James I. Mueller.
2. Summary of James I. Mueller's history at the University of Washington.
3. Summary of James I. Mueller's accomplishments and awards.
4. The numerous toughening concepts can be generalized into three basic mechanisms.
5. Enumeration of the predominant toughening concepts.
6. Illustration of the stress reduction (central region) and stress intensification (fiber tips) that occurs in a sapphire whisker reinforced polymer: from D. M. Schuster, "Single and Multi-Fiber Interactions in Discontinuously Reinforced Composites." Ph.D. thesis, Cornell University (1967).
7. Illustration of crack bridging configuration for slipping fibers: adapted from A. G. Evans and R. M. McMeeking, "On the Toughening of Ceramics by Strong Reinforcements," Acta Met., 34 (12) 2435-41 (1986).
8. Illustration of crack bridging configuration for strong particles: adapted from ibid.
9. Illustration of crack bridging configuration with ductile particles: adapted from ibid.
10. Illustration of the crack bowing concept: adapted from F. F. Lange, "The Interaction of a Crack Front with a Second-Phase Dispersion," Philos. Mag., 22 983-92 (1970).
11. Illustration of crack deflection around rods of two aspect ratios (R): from K. T. Faber and A. G. Evans, "Crack Deflection Processes - I. Theory," Acta Met., 31 565-76 (1983).
12. Idealized microcrack process zone around tip of main crack: adapted from R. W. Rice, "Mechanisms of Toughening in Ceramic Composites," Ceram. Eng. Sci. Proc., 2 (7-8) 661-701 (1981).
13. "Doc's" likely response to this lecture.

Table 1. Influence of Fiber Parameters on the Toughness of Ceramic Matrix Composites

Mechanisms	Fiber Parameters							Resid. Stress Param.		Influence on Composite K_{IC}
	l/d	V_f	$d=2r_f$	σ_f	τ	f-spac	K_{IC}	E_f/E_m	α_f/α_m	
Modulus Transfer	---	1	---	1	1	---	---	≥ 2	---	1
Fiber Pull-Out	Max K_{IC} $(l/d)_{cr} = \sigma_f/2\tau$	1	1	1	1	---	---	-important-		1
Crack Bridging	---	1	1	1	strong (but limited)	---	*	-important-		1
Crack Arresting/Blunting	---	"1"	---	---	---	"1"	"1"	-important-		1
Crack Bowing	---	1	"1"	---	---	1	"1"	-important-		1
Crack Deflection	1 (sat. @12)	1 (sat. @20)	indep. (controversial)	---	no predict. (but important)	---	---	-important-		1
Matrix Microcracking	---	1	1	---	---	---	---	"<1"	"<1"	1

Note 1: l/d = fiber length-to-diameter ratio, V_f = fiber volume fraction, d = fiber diameter, r_f = fiber radius, σ_f = fiber tensile strength, τ = fiber-matrix interfacial shear strength, f-spac. = distance between fibers, K_{IC} = fiber fracture toughness, E_f = fiber Young's modulus, E_m = matrix Young's modulus, α_f = fiber coefficient of thermal expansion, α_m = matrix coefficient of thermal expansion, K_{IC} = critical stress intensity (toughness) of composite

Note 2: Symbols surrounded by quotations represent intuitive predictions, all other predictions are the result of theoretical models.

*The importance of the fiber toughness depends on the type of crack bridging mechanism that is operating.




VITA

Born: June 26, 1916, Cincinnati, OH

Parents: August L. , Lydia (Heyn)

Education: B. S. in Ceramic Engineering,
Ohio State University, 1939

Ph. D. in Ceramic Engineering,
University of Missouri-Rolla,
1949



JAMES I. MUELLER ("DOC")

UNIVERSITY OF WASHINGTON

- Assistant Professor, 1949
- Associate Professor, 1951
- Professor, 1953
- Instrumental in the creation of the Ceramic Engineering Division within the Department of Mining, Metallurgical and Ceramic Engineering.

LER

- **Creator of the University of Washington Thermal Design Program, which commenced in 1972**
- **Awarded NASA's Public Service Medal in 1981 for his work on the Space Shuttle's thermal protection system.**

NASA

- **American Ceramic Society : Fellow
Distinguished Life Member
President, 1981-82**

BASIC TOUGHENING MECHANISMS

- **Increase the local driving force necessary for crack propagation**
- **Increase the mechanical energy consumed per unit area of crack propagation**
- **Decrease the local strain by cracking, which reduces the crack tip stress concentration**

1/1/00
J. K. Knowles


TOUGHENING CONCEPTS PROPOSED FOR CERAMIC MATRIX COMPOSITES

- | | |
|-------------------------------------|--------------------------------|
| 1. Modulus Transfer | 6. Crack Arresting |
| 2. Residual Stress | 7. Crack Bowing |
| 3. Transformation Toughening | 8. Crack Deflection |
| 4. Fiber Pull-Out | 9. Matrix Microcracking |
| 5. Crack Bridging | |

Fig. 1

- Delete 4D. n. 55. n
- Delete eq. below


FRICTIONAL BRIDGING



$$K_c \approx (\sigma_f^3 G / 3 E_f \tau)^{\frac{1}{2}} \sqrt{r_f A_f}$$

STRONG PARTICLE BRIDGING


- σ_f (MPa) = 1.0
- σ_f (MPa) = 1.0



$$K_c \approx 1.1 \sigma_f \sqrt{r_f A_f (1 - \sqrt{A_f}) (1 - A_f)}$$


- Ductile particles
- Ductile particles
- Ductile particles

DUCTILE PARTICLE BRIDGING





$$K_c \approx \sqrt{\Omega CA_f \sigma_y Gr_f (0.5 + \exp(\epsilon_f))}$$

Fig. 3



CRACK DEFLECTION PRODUCES A NON-PLANAR (TWISTED) CRACK







"So, what are you doing sitting
on your ?! Get out
there and do something!"

"Doc"
circa 1949 - 86